



**SPECIAL<sup>TM</sup>  
STEEL**  
The stars of Tool Steel

# DATA SHEET



**ANTARES<sup>TM</sup>**  
Hot Work  
Tool Steel

## ABOUT US

RR Special Steel combines the experience & know-how of two specialists in their respective fields, Steel Making and Remelting (Rubiera Special Steel) and Forging and Heat Treatment (Ringmill).



### RUBIERA SPECIAL STEEL

Since 1965 supplying high integrity ingots with superb homogeneity and cleanliness and since 2009 top quality large size ESR and VAR ingots to the market.



### RINGMILL

Since 1978 supplying top quality forgings to the most demanding markets using the latest state of the art technologies and machinery.

With RR Special Steel the ownership family, with a centenary experience in the steel and forging industry, has created the stars of tool steel.

## RR SPECIAL STEEL UNIQUENESS

**VAR:** The largest top-quality Vacuum Arc Remelted materials on the market.

**ESR:** The largest single electrode static Electro Slag Remelted materials on the market.

	Conventional material	ESR material	VAR material
Cleanliness	● ● ●	● ● ● ●	● ● ● ● ●
Homogeneity	● ● ●	● ● ● ● ●	● ● ● ● ●
Isotropy of toughness	● ●	● ● ● ●	● ● ● ● ●
Manufacturing complexity	● ● ●	● ● ● ●	● ● ● ● ●

## CERTIFICATE QUALITY

Manufacturing parameters and material properties are monitored and controlled by RR's quality management system. The results of cleanliness, microstructure, and toughness for example are available for internal- and external certification at any time.

## REFERENCE COMPOSITION OF STEEL GRADE RR ANTARES / 1.2344MOD.

C	Si	Cr	Mo	V
0.4 %	0.9 %	5.0 %	1.35 %	0.95 %

Comparable tool steel grades: NADCA #207 type B

## MATERIAL PROPERTIES

- Good resistance to thermal shock and heat cracking
- Good mechanical characteristics and toughness in hot condition, constant hardness throughout the production cycle
- Excellent machinability, high micro-purity level, good suitability for polishing and texturing
- Possibility to carry out welding operation with TIG (Tungsten Inert Gas) or MMA (Manual Metal Arc) methods
- Possibility of coating with PVD or PA/CVD methods, flame/induction hardening and nitriding.


## APPLICATIONS

- Dies for aluminium die-casting
- Dies subject to low pressure
- Chill moulds for gravity casting
- Containers for die-casting presses
- Dies for aluminium extrusion
- Extrusion press blocks
- Sleeves for extrusion
- Injection moulds
- Tools for plastic industry
- Rolls for profiling tools

PROPERTIES	STEEL GRADE*	1	2	3	4	5	
Toughness & Ductility	ANTARES	●	●	●	●		Very good toughness and ductility due to homogeneity and isotropy. According to NADCA #207 Charpy-V is guaranteed. Standard Charpy-V toughness is about 17J at 44-46 HRC and room temperature.
	1.2343	●	●	●	●		
	1.2344	●	●	●			
	1.2367	●	●				
Tempering Resistance	ANTARES	●	●	●			Good high-temperatures properties. High resistance against softening improves life time.
	1.2343	●	●				
	1.2344	●	●	●			
	1.2367	●	●	●	●	●	
Heat Checking Resistance	ANTARES	●	●	●	●		High toughness gives better crack resistance under thermal shock conditions during operations.
	1.2343	●	●	●			
	1.2344	●	●				
	1.2367	●	●	●			
Erosion & Hot Wear Resistance	ANTARES	●	●	●			Tempering resistance helps against wear and erosion. Optimizing of design and process parameter and nitriding/coating may be decisive factors as well.
	1.2343	●	●				
	1.2344	●	●	●			
	1.2367	●	●	●	●	●	
Resistance to Al sticking (Soldering)	ANTARES	●	●	●			Sticking means that the temperature is high at that region. Try to decrease temperature or/and use nitriding or coating.
	1.2343	●	●	●			
	1.2344	●	●	●			
	1.2367	●	●	●			
Machinability	ANTARES	●	●	●	●		Tough material can be even more tough in machining - optimize machining parameters.
	1.2343	●	●	●	●		
	1.2344	●	●	●	●		
	1.2367	●	●	●			
Polishability	ANTARES	●	●	●	●		ISO/SPI: NO/A-1 at 48-52 HRC: "lense quality". Keep attention on right polishing steps.
	1.2343	●	●	●	●		
	1.2344	●	●	●			
	1.2367	●	●				
Weldability	ANTARES	●	●	●			CET= 0.85% acc. DIN EN 1011-2: pre- and after-heating necessary.
	1.2343	●	●	●			
	1.2344	●	●	●			
	1.2367	●	●				
Texturability	ANTARES	●	●	●	●		Hardened and homogeneous material is excellent for texturing.
	1.2343	●	●	●	●		
	1.2344	●	●	●			
	1.2367	●	●	●			
Nitridability	ANTARES	●	●	●	●		Hardness of nitrided surface 900-1250 HV1: avoid brittle surface layer.
	1.2343	●	●	●			
	1.2344	●	●	●	●		
	1.2367	●	●	●	●		
Chrome Plating Ability	ANTARES	●	●	●	●		High cleanliness improves Cr plating ability.
	1.2343	●	●	●	●		
	1.2344	●	●	●			
	1.2367	●	●	●			

\*All grades in the remelted condition

## PRODUCTION TECHNOLOGY



## PRODUCT RANGE

	Form	Thickness (mm)	Width (mm)	Length (mm)	Weight (Kg)
RR ANTARES	Square/Rectangular Bar	max. 600	max. 1,500	max. 6,000	max. 20,000
	Round Bar	max. 700	N/A	max. 6,000	max. 20,000

## DELIVERY CONDITIONS


**Heat treatment:** EFS Annealing

**Hardness:**  $\leq 220$  HBW


**Surface:** machined

## PHYSICAL PROPERTIES


### MICROGRAPHIC EXAMINATION IN EXTRA FINE ANNEALED CONDITION (EFS)



EFS macrostructure at 50X: very low microsegregation of ESR material



EFS microstructure at 500X: AS1-2 rating



\* The examined surface is parallel to the principal direction of deformation

	20°C	400°C	500°C
Elastic Modulus [kN/mm <sup>2</sup> ]	205,000	--	190,000
Thermal Expansion Coefficient [10 <sup>-6</sup> /K]	--	12.4	13.2
Thermal Conductivity [W/mK]	21	30	32


HEAT TREATMENT	TEMPERATURE
Soft Annealing	780-830°C
Stress Relieving (before Q+T)	600-650°C
Hardening (Vacuum)	1020-1040°C
Tempering (2-3X)	580-630°C

## MECHANICAL PROPERTIES AFTER QT

HARDNESS	44 HRC	48 HRC	50 HRC
Yield Strength Rp02 [N/mm <sup>2</sup> ]	~ 1,200	~ 1,400	~ 1,500
Tensile Strength, Rm [N/mm <sup>2</sup> ]	~ 1,500	~ 1,680	~ 1,800


### Toughness Properties

Chapy-V toughness on oil-hardened & double tempered samples, 44-46 HRC, transversal direction, 1/4T, 20°C.




## DIAGRAMS


### TEMPERING DIAGRAM



### CCT DIAGRAM



### TTT DIAGRAM





**SPECIAL<sup>TM</sup>**  
**STEEL**  
The stars of Tool Steel



**ANTARES<sup>TM</sup>**  
Hot Work  
Tool Steel

**Ring Mill SpA**  
Via Valeriana, 103 | 23015 Dubino (SO) - Italy  
VAT IT00122100142 | Ph. +39 0342 688111  
**RR Special Steel is a Ring Mill trademark**

© RINGMILL SpA 2021 - All rights reserved. This brochure may not be, entirely or partially, reproduced, copied, distributed or modified, without the explicit authorization by Ring Mill SpA. In particular, it is prohibited to alter the contents and/or use, any information provided herein, out of context. All information provided herein is for general information purposes only. Further information may be obtained writing at [info@ringmill.it](mailto:info@ringmill.it).